

EN: This Datasheet is presented by the manufacturer.

Please visit our website for pricing and availability at www.hestore.hu.



ul. Harcerska 8, 18-100 Łapy, tel. 085 715 33 28, fax 085 715 76 81
PKO BP S.A. 96 1020 1332 0000 1502 0324 0447
NIP: 966-176-77-14, REGON: 200133730
www.termopasty.pl, e-mail: biuro@termopasty.pl

Product Data Sheet

Heat conductive silicone paste

It facilitates heat transfer between the electronic components and radiator. It is necessary for correct operation of any type of temperature sensors. It protects from weather conditions and prevents from breakthrough. It is characterized by very good chemical resistance for oxidation, water solutions of acids, alkalis and salts, sulphur dioxide and ammonia. It has a very wide range of work temperatures.



Properties:

Density at. 20°C: 1,47 g/cm³

Flash point: 350°C

Freezing point: -50°C

Refraction coefficient: 1,405

Specific heat at 50°C: 0,243 Cal /g K

Overall heat-transfer coefficient at 0-50°C:0,88 W/m K,

Dielectric constant at 100 Hz: $4,7 (\pm 0,1)$

Cross-through resistance: 5 x 10¹⁴ Ohm x cm

Loss tangent at f = 100 Hz: 0,020 (±0,003),

Operating temperature range: -50~200°C

Package:

| Weight | Package | Symbol |
|------------------|---------|---------|
| 7 g (metal tube) | 10 | AGT-055 |
| 25 g (syringe) | 2 or 16 | AGT-056 |
| 100 g (jar) | 6 or 36 | AGT-057 |
| 1000 g (jar) | 1 | AGT-058 |
| 5000 g (pail) | 1 | AGT-059 |

